

Similar Standards

JIS Specification And Grade			BS Specification And Grade	DIN Specification And Grade	Steel Composition
Marking Symbol	Pipe	Plate	Pipe	Pipe	
F50P or 50P PG370(W), PS370(W), PT370 PG410(W), PS410(W), PT410(W), PT410 PS370, PT370(W) PS410, PT410(W) PS480, PT480(W)	SCPSTP1000	S5400	1387 M	2440-ST33-1	Carbon Steel
	STPG370	SM41B	3602-ERW23	1626-ST37	Carbon Steel
	STPG410	SM41B	3602-ERW27	-	Carbon Steel
	STPT370	SB42	3602-Steel23	17175-ST35.8	Carbon Steel
	STPT410	SB42	3602-Steel27	17175-ST35.8	Carbon Steel
STPT480	SB49	3602-Steel35	1	Carbon Steel	
PL380(W) PL450(W) PL680(W)	STPL380	-	3603-Steel27 LT 30	-	Carbon Steel
	STPL450	-	3603-Steel03 LT100	-	35% Ni Steel
	STPL680	-	-	-	2% Ni 1% Cu Steel
PA12(W), FA12 PA20(W), FA20 PA23(W), FA23 PA24(W), FA24 PA25(W), FA25 - PA26(W), FA26	STPA12	-	-	17175-15 Mo3	Carbon-Molybdenum Steel
	STPA22	-	3603-HF020	17175-13 Cr Mo44	1% Cr-1/2% Molybdenum Steel
	STPA23	-	3603-HF021	-	11% Cr-1/2% Molybdenum Steel
	STPA24	SCM44	3603-HF022.27	17175-10 Cr Mo910	2% Cr-1% Molybdenum Steel
	STPA25	-	3603-HF025	-	5% Cr-1/2% Molybdenum Steel
	-	-	-	-	7% Cr-1/2% Molybdenum Steel
	STPA26	-	-	-	9% Cr-1/2% Molybdenum Steel
SUS304, SUS304W, SUS304F SUS304H, SUS304HF SUS304L, SUS304LW SUS306, SUS306W, SUS306F SUS310S, SUS310W, SUS310F SUS316, SUS316W, SUS316F SUS316H, SUS316HF SUS316L, SUS316LW SUS317L SUS321, SUS321W, SUS321F SUS321H, SUS321HF SUS347, SUS347W, SUS347F SUS347H, SUS347HF	SUS304TP	SUS304	3605-801	17140.X5 Cr Ni19	18% Cr-8% Ni Steel
	SUS304HTP	-	3605-811	-	18% Cr-8% Ni-0.04-0.10% C Steel
	SUS304LTP	SUS304L	3605-811L	17140.X2 Cr Ni19	18% Ni-0.035% C Steel
	SUS306STP	SUS306	-	-	22% Cr-12% Ni Steel
	SUS310STP	SUS310S	3605-805S	-	25% Cr-20% Ni Steel
	SUS316TP	SUS316	3605-845	17140.X5 Cr Ni Mo1810	16% Cr-8% Ni-Mo Steel
	SUS316HTP	-	3605-855	-	18% Cr-8% Ni-Mo-0.04-0.10% C Steel
	SUS316LTP	SUS316L	3605-845L	17140.X2 Cr Ni Mo1810	18% Cr-8% Ni-Mo-0.035% C Steel
	SUS317LTP	SUS317L	-	-	19% Cr-12% Ni-3.5% Mo-Low C
	SUS321TP	SUS321	3605-822T1	17140.X10 Cr Ni Ti19	18% Cr-8% Ni-Ti Steel
	SUS321HTP	-	3605-832T1	-	18% Cr-8% Ni-Ti-0.04-0.10% C Steel
	SUS347TP	SUS347	3605-822Nb	17140.X1 Cr Ni Nb19	18% Cr-8% Ni-Cb+Ta Steel
	SUS347HTP	-	3605-832Nb	-	18% Cr-8% Ni-Cb+Ta-0.04-0.10% C Steel