

JIS Specification And Grade			BS Specification And Grade	DIN Specification And Grade	Steel Composition
Marking Symbol	Pipe	Plate	Pipe	Pipe	
F50P or SGP PG370(W), PS370(W), PT370 PG410(W), PS410(W), PT410(W), PT410 PS370, PT370(W) PS410, PT410(W) PS480, PT480(W)	SGP(STPY600)	SS400	1387 M	2440-ST33-1	Carbon Steel
	STPG370	SM41B	3602-ERW23	1626-ST37	Carbon Steel
	STPG410	SM41B	3602-ERW27	-	Carbon Steel
	STPT370	SB42	3602-Steel23	17175-ST35.8	Carbon Steel
	STPT410	SB42	3602-Steel27	17175-ST35.8	Carbon Steel
	STPT480	SB49	3602-Steel35	1	Carbon Steel
PL380(W) PL450(W) PL680(W)	STPL380	-	3603-Steel27 LT 30	-	Carbon Steel
	STPL450	-	3603-Steel30 LT100	-	31% Ni Steel
	STPL680	-	-	-	2% Ni 1% Cu Steel
PK12(W), FA12 PK20(W), FA22 PK23(W), FA23 PK26(W), FA24 PK25(W), FA25 - PK26(W), FA26	STPK12	-	-	17175-15 Mo3	Carbon-Molybdenum Steel
	STPK22	-	3603-HF420	17175-13 Cr Mo44	1% Cr-1% Molybdenum Steel
	STPK23	-	3603-HF421	-	11% Cr-1% Molybdenum Steel
	STPK24	SCM414	3603-HF422.27	17175-10 Cr Mo410	25% Cr-1% Molybdenum Steel
	STPK25	-	3603-HF425	-	5% Cr-1% Molybdenum Steel
	-	-	-	-	7% Cr-1% Molybdenum Steel
	STPK26	-	-	-	9% Cr-1% Molybdenum Steel
SUS304, SUS304W, SUS304F SUS304H, SUS304HF SUS304L, SUS304LW SUS308, SUS308W, SUS308F SUS310S, SUS310W, SUS310F SUS316, SUS316W, SUS316F SUS316H, SUS316HF SUS316L, SUS316LW SUS317L SUS321, SUS321W, SUS321F SUS321H, SUS321HF SUS347, SUS347W, SUS347F SUS347H, SUS347HF	SUS304TP	SUS304	3605-801	17140-X5 Cr Ni189	18% Cr-8% Ni Steel
	SUS304HTP	-	3605-811	-	18% Cr-8% Ni-0.01-0.10% C Steel
	SUS304LTP	SUS304L	3605-811L	17140-X2 Cr Ni189	18% Ni-0.035% C Steel
	SUS308STP	SUS308S	-	-	22% Cr-12% Ni Steel
	SUS310STP	SUS310S	3605-805S	-	25% Cr-20% Ni Steel
	SUS316TP	SUS316	3605-845	17140-X5 Cr Ni Mo1810	18% Cr-8% Ni-Mo Steel
	SUS316HTP	-	3605-855	-	18% Cr-8% Ni-Mo-0.01-0.10% C Steel
	SUS316LTP	SUS316L	3605-845L	17140-X2 Cr Ni Mo1810	18% Cr-8% Ni-Mo-0.035% C Steel
	SUS317LTP	SUS317L	-	-	18% Cr-12% Ni-3.5% Mo-Low C
	SUS321TP	SUS321	3605-822Ti	17140-X19 Cr Ni Ti189	18% Cr-8% Ni-Ti Steel
	SUS321HTP	-	3605-832Ti	-	18% Cr-8% Ni-Ti-0.01-0.10% C Steel
	SUS347TP	SUS347	3605-832Nb	17140-X1 Cr Ni Nb189	18% Cr-8% Ni-Cb+Ta Steel
	SUS347HTP	-	3605-832Nb	-	18% Cr-8% Ni-Cb-5x0.01-0.10% C Steel